

CHEMICAL PRODUCT	RUBBER								
	Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Acetamide				3	2	2	1	2	1
Acetic acid	10 %	50		4	4	4	2	2	3
Acetic acid	50 %	50		4	3	4	3	3	4
Acetic acid conc.				4	2	3	2	3	1
Acetic anhydride				2	4	1	2	1	2
Acetone				1	4	2	1	3	1
Acetyl chloride						4		4	4
Acetylene				1	1	2	1	2	1
Acrylonitrile		50		4	4	2	4	3	3
Adipic acide					1				
Alum, aqueous		65		1	1	1	1	1	1
Aluminium chloride, aqueous		65		1	1	1	1	1	1
Aluminium flouride		65		1	1	1	1	1	1
Aluminiums sulfate, aqueous		65		1	1	1	1	1	1
Ammoium chloride, aqueous				1	1	1	1	1	1
Ammonia				1	1	1	1	1	1
Ammonia liquid							2	4	1
Ammonium carbonate		70		1	4	2	1		1
Ammonium hydroxide, solution of				1	2	1	1	1	1
Ammonium nitrate, aqueous				1	1	1	1	1	1
Ammonium phosphate, aqueous				1	1	1	1	1	1
Ammonium sulfate, aqueous				1	1	1	1	1	1
Amyl acetate				4	4	4	2	4	2
Amyl alcohol		50		1	2	1	1	1	1
Amyl borate				4	1	1	4		4
Amyl chloronaphtene				4	4	3	4	4	4
Amyl naphtalene				4	3	4	4	4	4
Aniline				2	4	3	2	4	1
Aniline hydrochloride				3	2	4	2	4	2
Aniline oil				4	4	3	1	4	3
Animal oil		50		4	1	2	2	2	2
Ansul ether				4	3	4	3	4	3
Arsenic acid						1	1	1	1
Asphalt		100		4	2	3	4	3	4
Barium chloride, aqueous		100		1	1	1	1	1	1
Barium hydroxide		100		1	1	1	1	1	1
Barium sulfide		100		1	1	1	1	1	1
Beer				1	1	1	1	1	1
Beet sugar solution				1	1	1	1	1	1
Benzaldehyde				4	4	4	2	4	1
Benzene				4	4	4	4	4	4
Benzine				4	1	4	4	4	4

Semperit Technische Produkte Gesellschaft m.b.H. & Co KG  
A-2632 Wimpassing, Triester Bundesstraße 26  
Telefon +43 2630 310-0\*, Telefax +43 2630 310 320  
E-Mail: semperflex@semperit.at, Internet: www.semperit.at