

CHEMICAL PRODUCT			RUBBER					
Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Sodium phosphates			2	2	3	1	1	1
Sodium silicate			1	1	1	1	1	1
Sodium sulfate			1	1	1	1	1	1
Sodium sulphite			1	1	1	1	1	1
Sodium thiosulfate, aqueous			1	1	1	1	1	1
Soybean oil			3	1	2	3	2	3
Stannic (II) chloride, aqueous			1	1	1	2	1	2
Steam		120	3	1	2	1	2	1
Stearic acid		70	3	2	2	4	2	2
Styrene		23	4	4	4	4	4	4
Sugar solutions			1	1	1	1	1	1
Sulfur			4	4	1	1	1	1
Sulfur chloride			4	3	3	4	1	4
Sulfur dichloride			4	3	3	4	2	
Sulfur dioxide			3	3	3	2	4	1
Sulfur hexaflouride			1	1	1	1	2	1
Sulfur trioxide			3	3	3	3	2	3
Sulfuric acid	5-10 %	100	1	3	1	1	1	1
Sulfuric acid	10-50 %		1	1	1	1	1	3
Sulfuric acid	50-80 %	100	3	4	4	1	4	
Sulfuric acid fuming Oleum	20 %		4	4	4	4	4	4
Sulfurous acid			2	2	2	1	1	2
Tannic acid			2	1	1	1	1	1
Tar			4	2	3	4	3	4
Tartaric acid, aqueous		100	1	1	1	1	1	2
Test fuel B			4	2	3	4	3	4
Test fuel C			4	2	4	4	4	4
Tetrabromomethane			4	4		4		4
Tetrabutyl titanate			2	1	1	2		1
Tetrachlorethane				4		4		
Tetrahydrofurane			4	4	4	4	4	4
Tetralin			4	4	4	4	4	4
Thionyl chloride			4		4	4	4	4
Titanium tetrachloride			4	3	4	4	4	4
Toluene			4	4	4	4	4	4
Toluene diisocyanate		70	3		4	1	4	1
Transformer oil			4	1	2	4	3	4
Triacetin			3	2	2	1	2	1
Triaryl phosphate			4	4	3	1	3	1
Tributoxy ethyl phosphate			3	4	4	2	4	2
Tributyl phosphate		100	3	4	4	3	4	1
Trichloroacetat acid		20		2	2	2	2	2