

CHEMICAL PRODUCT	RUBBER								
	Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Trichloroethane (1, 1, 1)				4	4	4	4	4	4
Trichloroethylene				4	4	4	4	4	4
Tricresyl phosphate		70		3	4	4	1	4	1
Triethynol amine				2	3	1	2	1	2
Triethyl amine				4	1	3	4	3	4
Triethyl borane		70				4		4	3
Trinitrotoluene				4	4	2	4	2	4
Trioctyl phosphate				4	4	4	1	4	1
Turpentine				4	1	4	4	4	4
Turpentine oil				4	1	4	3	4	3
Varnishes				4	4	4	3	4	4
Vegetable oils				4	1	2	2	2	2
Vinegar				3	3	3	1	1	1
Vinyl acetylene		-20		2		2	1	2	1
Vinyl chloride monomer						4		4	2
Water				1	1	2	1	1	1
Water, distilled		100		1	1	2	1	2	1
Whisky and wines				1	3	1	1	1	1
Wood oil				4	1	2	1	2	1
Xylene, mixture of isomers				4	4	4	4	4	4
Zinc chloride				3	3	3	1	1	1
Zinc sulfate				1	1	1	1	1	1