

CHEMICAL PRODUCT	RUBBER								
	Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Chile salpêtre				1	1	1	1	1	1
Chlorinated solvents				4	4	4	4	4	4
Chlorine				3	4	3	3	2	3
Chlorine dioxide					4	4	4	2	3
Chlorine trifluoride					4	4	3	4	4
Chlorine water	3 %			4	4	4	4	3	4
Chloro nitro ethane				4	4	4	4	4	
Chloroacetic acid				3	3	2	2	2	2
Chloroacetone					4	3	3	3	1
Chlorobenzene		50		4	4	4	4	4	4
Chlorobromomethane				4	4	4	4	4	4
Chlorododecane				4	4	4	4		4
Chloroform				4	4	4	4	4	4
Chloronaphtaline				4	4	4	4	4	4
Chloroprene				4	4	4	4	4	4
Chlorosulfonic acid				4	4	4	4	4	4
Chlortoluol				4	4	4	4	4	4
Chromic acid, solution	10-50 %	50		4	4	4	3	1	4
Citric acid		70		1	1	1	1	1	1
Coconut oil				4	1	2	2	3	2
Cod liver oil				4	1	2	2	2	2
Coke-oven gas				2	2	2	1	2	4
Copper (II) chloride		65		1	1	2	1	2	1
Copper (II) sulfate		65		1	1	1	2	1	1
Corn oil				4	1	3	2	3	2
Cottonseed oil		70		4	1	3	1	3	2
Creosote				4	2	3	4	3	4
Cresol i-		70		4	4	4	1	4	2
Cumene						4		4	
Cyclohexane				4	1	3	4	3	4
Cyclohexanol				4	2	1	4	1	4
Cyclohexanone				4	4	4	3	4	1
Cymene				4	4	4	4	4	4
Decalin cis-/trans-				4		4		4	
Decane				4	4	4	4	4	
Diacetone							1		1
Diacetone alcohol				4	4	1	1	1	1
Dibenzyl ether				4	4	4	1	4	2
Dibenzyl sebacate						4	2		2
Dibutyl amine				4	4	4	4	4	4
Dibutyl ether				4	3	3	3	3	3
Dibutyl phthalate				4	4	4	2	4	1