

CHEMICAL PRODUCT			RUBBER					
Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Dibutyl sebacate			4	4	4	2	4	2
Dichlore isopropyl ether			4	4	4	3	4	3
Dichlorobenzene			4	4	4	4	4	4
Dicyclohexylamine			4	2	4	4	4	4
Diesel fuel			4	1	3	4	3	4
Diethyl amine			4	2	3	4	3	4
Diethyl benzene			4	4	4	4	4	4
Diethyl sebacate				4	4	2	4	2
Diethylene glycol		100	1	1	1	1	1	1
Diisobutylene (mixture of isomers)				2	3		3	
Diisopropyl benzene			4	4	4	4	4	4
Diisopropyl ketone			4	4	4	2	4	2
Dimethyl aniline			4	4	4	2	4	2
Dimethyl formamide N, N-			2	2	4	2-3	2	2
Dimethyl phtalate			4	4	4	2	4	2
Dinitrotoluene			4	4	4	4	4	4
Diocetyl phthalate		100	4	3	4	3	4	2
Diocetyl sebacate			4	3	4	2	4	2
Dioxane			4	4	4	2	4	
Dioxolane			4	4	4	3	4	2
Dipentene			4	2	4	4	4	4
Diphenyl		70	4	4	4	4	4	4
Diphenyl oxide			4	4	4	4	4	1
Epichlorohydrin		50	4	4	4	3	4	2
Ethanol		50	1	1	1	1	1	1
Ethanolamine		70	1	1	2	1	3	1
Ether			4	2	4	3	3	3
Ethyl acrylate				4	4	2	4	2
Ethyl benzene			4	4	4	4	4	4
Ethyl benzoate						2		2
Ethyl chloride			2	2	2	1	4	1
Ethyl chlorocarbonate			4		3	2	3	
Ethyl chloroformiate					3		3	
Ethyl formiate			4	4	2	2	2	2
Ethyl glycol			3	1	1	1		2
Ethyl glycol acetate			3	4	4	1	4	1
Ethyl mercaptane			4	4	4	4	2	4
Ethyl oxalate			1	4	3	1	4	1
Ethyl pentachlorobenzene			4	3	4	4	4	4
Ethyl silicate			2	1	1	1	2	1
Ethylacetate			3	4	3	2	3	1
Ethylacetoacetate			3	4	3	2	4	2