

CHEMICAL PRODUCT	RUBBER								
	Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Ethylcellulose				1	1	1	2		2
Ethylene					1				
Ethylene chloride				4	4	4	3	4	2
Ethylene chlorohydrine				3	4	1	1	2	
Ethylene diamine				2	1	1	1	2	1
Ethylene glycol		100		1	1	2	1	2	1
Ethylene oxide					4	4	3	4	3
FCKW 12				4	2	1	2	1	2
FKW 125				3	1	3	3	1	1
FKW 134A				2	1	2	3	1	1
Fluid 101		100		4	1	4	4	4	4
Fluorine, liquid						4	3		3
Fluoro benzene				4	4	4	4		4
Fluoroboric acid				1	1	1	1	1	1
Fluorochloro etylene					4		3		
Formaldehyde	40 %			1	1	1	1	1	1
Formic acid	10 %	60		2	2	2	1	2	2
Formic acid		70		2	3	3	2	3	2
Freon 11				2	1	1	4	1	4
Freon 112				4	2	3	4	2	4
Freon 113				2	1	1	3	1	3
Freon 114				1	1	1	1	1	1
Freon 114 B2				3	2	1	4	1	4
Freon 115				1	1	1	1	1	1
Freon 13 B1				1	1	1	1	1	1
Freon 142 B				1	1	1	1	1	1
Freon 152 A				1	1	1	1	3	1
Freon 21				4	4	3	3	4	3
Freon 218				1	1	1	1	1	1
Freon 22				1	3	1	1	1	1
Freon 31				2	4	1	1	2	1
Freon 316 C				1	1	1	1	1	1
Freon 318 C				1	1	1	1	1	1
Freon 32				1	1	1	1	1	1
Freon 502					1	2			4
Freon BF				4	2	2	4	2	
Freon MF				2	1	3	4	4	
Freon TA				1	1	1	1	1	1
Freon TC				2	1	1	1	1	2
Freon TF				2	4	4	4	4	4
Freon TMC				3	2	2	2	2	2
Freon T-P 35				1	1	1	1	1	1