

CHEMICAL PRODUCT			RUBBER					
Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Freon T-WD 602			2	2	2	1	2	2
Fuel oil		70	4	1	2	4	2	4
Fumaric acid			1	1	2	4	2	
Furan			4	4	4	3	4	3
Furfural			3	4	4	2	3	2
Gallic acid			2	3	2	1	2	2
Gasohol			4	3	4	4		4
Gelatine, aquaeous			1	1	1	1	1	1
Glucose			1	1	1	1	1	1
Glycerol (glycerine)		100	1	1	1	1	1	1
Green liquor			1	1	1	1	1	1
Hexachlorobutadiene			4	1	4	4	4	4
Hexaldehyde			4	4	1	1	3	1
Hexane n-			4	1	1	4	2	4
Hexanol			1	1	2	2	2	3
Hexene			4	2	2	4	2	4
Hydraulic oil, glycol-based			1	1	1	1	1	1
Hydraulic oil, mineral oil			4	1	1	4	2	4
Hydraulic oil, phosphate ester			4	4	3	1	4	1
Hydraulic oil, silicate ester			4	3	3	4	3	4
Hydrazine				2	2	1	2	1
Hydrobromid acid			2	4	2	1	1	1
Hydrochloric acid	10 %	100	3	3	1	2	1	4
Hydrochlorid acid	20 %	50	2	2	1	1	1	2
Hydrocyanic acid	37 %		2	2	1	1	1	1
Hydrofluoric acid	50 %		3	3	1	1	1	1
Hydrofluoric acid	75 %		3	4	3	1	1	
Hydrofluoric acid, anhydrous				4	1	1		3
Hydrogen			1	1	1	1	1	1
Hydrogen peroxide	30 %		1	1	1	1	1	1
Hydrogen peroxide	85 %		4	4	4	3	3	3
Hydrogen sulfide			1	4	1	1	2	1
Hydroquinone			2	3				
Hypochlorous acid			2	4	3	2	2	3
Inorganic salts		70	1	1	1	1	1	1
Iodine pentafluoride			4	4	4	4	4	4
Iodoform						1		1
Iron (II) sulfate		65	1	1	1	1	1	1
Iron (III) chloride		65	1	1	1	1	1	1
Isobutanol			1	2	1	1	1	1
Isooctane			3	1	1	4	2	4
Isophorone				4		1		1