

CHEMICAL PRODUCT	RUBBER								
	Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Isopropanol				2	2	1	1	1	1
Isopropyl acetate				4	4	4	2	4	2
Isopropyl chloride				4	4	4	4		4
Isopropyl ether				4	2	2	4	2	
Kerosene			70	4	1	3	4	3	4
Lactic acid			70	1	1	1	1	1	1
Lead sulphamate				2	2	2	1	2	1
Lead tetraethyl						2	4	4	4
Linoleic acid			70		2	4	4	4	4
Linseed oil				3	1	2	1	2	1
Lubricating oils			100	4	1	2	4	2	4
Magnesium chloride			65	1	1	1	1	1	1
Magnesium hydroxide				1	1	1	1	1	1
Magnesium sulfate, aqueous			65	1	1	1	1	1	1
Maleic acid				2	2	3	3	4	3
Maleic anhydride				2		3	3	4	3
Malic acid, aqueous				2	1	2	4	2	4
Mercury				1	1	1	1	1	1
Mercury chloride				2	2	3	1	1	1
Mesityl oxide				4	4	4	2	4	2
Metacrylic acid				4		2	2		2
Methane				4	1	1	4	2	4
Methanol			50	1	1	1	1	1	1
Methyl acetate				4	4	4	2	4	2
Methyl acrylate				4	4	4	2	4	2
Methyl bromide					2	4		4	
Methyl butyl ketone				4	4	4	2	4	2
Methyl chloride				4	4	4	3	4	3
Methyl cyclopentane				4		3	4		3
Methyl ethyl ketone									
see Ethyl methyl ketone				3	4	3	1	4	1
Methyl formiate				3	4	2	2	2	2
Methyl glykol acetate									
see Acetic acid -2- methoxy ethyl ester			50	2	4	3	1	2	
Methyl isobutyle ketone				4	4	4	2	4	2
Methyl isopropyle ketone				4	4	4	2	3	3
Methyl methacrylate				4	4	3	3	4	3
Methyl salicylate					4	4	2	4	2
Methylaniline				4	4	4		4	
Methylene chloride				4	4	4	3	4	3
Metyl oleate				4	4	4	2		2
Milk				1	1	1	1	1	1