

CHEMICAL PRODUCT			RUBBER					
Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
Mineral oil			3	1	2	4	2	4
Mineral oil ASTM Nr.I		100	3	1	1	4	1	4
Mineral oil ASTM Nr.II (IRM 902)		100	4	1	2	4	3	4
Mineral oil ASTM Nr.III (IRM 903)		100	4	1	4	4	4	4
Naphta			4	1	4	4	4	4
Naphtalene		80	4	4	4	4	4	4
Naphtanic acid			4	2		4		4
Natural gas			3	1	1	4	1	4
Nickel chloride		65	1	1	1	1	1	1
Nickel sulfate		65	1	1	1	1	1	1
Nitric acid	10 %	50	2	2	3	1	1	1
Nitric acid	60 %		4	4	4	4	2	4
Nitric acid fuming			4	4	4	4	4	4
Nitro benzene		50	4	4	4	1	4	1
Nitro ethane			2	4	3	2	2	2
Nitro methane			2	4	3	2	3	2
Nitro propane n-			3	4		1		1
Nitrogen			1	1	1	1	1	1
Nitrogen tetroxide			4	4	4	3	4	3
Octochlorotoluene			4	4	4	4	4	4
Octadecene			4	1	2	4	2	4
Octane			4			4		4
Octanol (1)			2	2	1	1	1	1
Oleic acid			4	1	4	4	3	3
Olive oil		50	3	1	2	2	2	3
Oxalic acid		70	1	3	2	1	1	1
Oxidising salt solutions		70			2		3	4
Oxige			3	1	1	1	1	1
Oxygen liquid				3		1		
Ozone		40	4	4	2	2	1	1
Palmitic acid			3	1	2	2	3	2
Perchloric acid				4	2	2	2	2
Perchloroethylene			4	3	4	4	4	4
Petroleum		95	4	1	2	4	3	4
Phenol		100	4	4	4	2	4	2
Phenyl ethyl ether			4	4	4	4	4	4
Phenyl hydrazine			3	4	3	3	4	2
Phorone			4	4	4	2	4	2
Phosphoric acid	50 %	50	1	3	2	1	1	1
Phosphoric acid, raw			3	3	3	3	1	3
Phosphorous trichloride			4	4	4	1		1
Picnc acid		100	2	2	1	2	1	2