

	CHEMICAL PRODUCT			RUBBER					
	Marking of the medium	Conc.	allowble working temp. °C	NR/SBR SBR	NBR	CR	CIIR	CSM	EPDM
	Pine oil		70	4	2	4	4	4	4
	Pinen		70	4	2	4	4	3	4
	Piperidine			4	4	4	4	4	4
	Potassium chloride			1	1	1	1	1	1
	Potassium cyanide			1	1	1	1	1	1
	Potassium hydroxide			2	3	3	1	1	1
	Potassium permanganate		70			2		3	4
	Potassium sulfate, aqueous			1	1	1	1	1	1
	Propane			4	1	2	4	2	4
	Propanol (1)		50	1	2	1	1	1	1
	Propene			4	3	4	4	4	4
	Propyl acetate			4	4	4	2	4	2
	Propyl nitrate					4	2	4	2
	Propylamine			4	4	4	3	4	3
	Propylene oxide			4		4	2	4	2
	Pydraul F-9		80	4	4	4	3	4	2
	Pyridine			4	4	4	1	4	2
	Pyrrole			3	4	4	4	4	3
	Rape seed oil		100	4	1	2	3	3	2
	Salicylic acid, aqueous				1	1	1		1
	Salt and salt solutions		70	1	1	1	1	1	1
	Sewage			3	1	2	3	1	2
	Silicate ester			4	2	1	4	1	4
	Silicofluoric acid			2	2	2	3	1	2
	Silicone grease				1	2	1	2	1
	Silicone oils				1	1	1	1	1
	Skydrol 500		70	4	4	4	2	4	1
	Skydrol 7000		70	4	4	4	2	4	1
	Soap solutions			1	1	1	1	1	1
	Sodium bicarbonate			1	1	1	1	1	1
	Sodium bisulphate			1	1	1	1	1	1
	Sodium carbonate		100	1	1	1	1	1	1
	Sodium chloride			1	1	1	1	1	1
	Sodium cyanide, solution of			1	1	1	1	1	1
	Sodium hydroxide			2	3	3	1	3	1
	Sodium hydroxide	10 %	100	1	1	1	1	1	1
	Sodium hydroxide	20 %	100	1	4	1	1	1	1
	Sodium hypochlorite			4	4	4	1	2	1
	Sodium metaphosphate			1	1	3	1	2	1
	Sodium nitrate			3	3	3	1	1	1
	Sodium perborate			3	3	3	1	1	1
	Sodium peroxide			2	3	2	1	2	1