





## PARA

## A 160 g

-  NR-SBR, grey – high-grade
-  highly elastic
-  excellent mechanical properties
-  packaging see General Information

Hardness [Shore A]:	40 ±5
Density [g/cm <sup>3</sup> ]:	1.08
Tensile strength [N/mm <sup>2</sup> ]:	15
Elongation at break [%]:	550
Ozone resistance:	non resistant
Weather resistance:	non resistant
Oil resistance:	non resistant
Benzine resistance:	non resistant
Acid resistance:	moderately resistant
Strong bases:	resistant
Abrasion resistance:	good suitable

## WORKING TEMPERATURE RANGE

Medium	dyn. (stat.)	max.	short-term
Air	-40 (-50) °C	+70 °C	+80 °C

## COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	70 °C	35 %

## AGING DIN 53508

Conditions	Hardness	Strength	Elongation
70h/70 °C	+3 Shore A	-15 %	-20 %

## AUMA-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
4011 63100	1.0	1.4	20	SS	0
4011 63150	1.5	1.4	20	SS	0
4011 63200	2.0	1.4	20	SS	0
4011 63300	3.0	1.4	10	SS	0
4011 63400	4.0	1.4	10	SS	0
4011 63500	5.0	1.4	10	SS	0
4011 63600	6.0	1.4	10	SS	0
4011 63800	8.0	1.4	5	SS	0

## PRESS-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
4213 63100	10.0	1.4	5	SS	0
4213 63120	12.0	1.4	5	SS	0
4213 63150	15.0	1.4	5	SS	0
4213 63200	20.0	1.4	5	SS	0
4213 63250	25.0	1.4	5	SS	0
4213 63300	30.0	1.4	5	SS	0
4213 63400	40.0	1.4	5	SS	0

S = smooth

Please Note:

22.8.2003

This catalogue has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this catalogue can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course guarantee the quality of our products according to our general sales conditions, available on request.

Subject to alteration without prior notice – All mentioned properties contained in this catalogue are guiding values representing longterm experience average.

Semperit Technische Produkte Gesellschaft m.b.H. & Co KG  
 A-2632 Wimpassing, Triester Bundesstraße 26  
 Telefon +43 2630 310-0\*, Telefax +43 2630 310 320  
 E-Mail: semperflex@semperit.at, Internet: www.semperit.at