

ABRASION

RED STAR + VKS

- Ⓢ NR-SBR, red – high-grade
- Ⓢ wear resistant quality, 40 Shore, with bonding layer (VKS)
- Ⓢ highly elastic
- Ⓢ typical operational areas: sand blast rooms, fine-granular materials
- Ⓢ thickness tolerances:
up to 6 mm thickness according to DIN 7715 P3;
over 6 mm according to ISO 3302 ST3
- Ⓢ packaging see General Information

Hardness [Shore A]:	40 ±5
Density [g/cm ³]:	1.06
Tensile strength [N/mm ²]:	16
Elongation at break [%]:	600
Abrasion [mm ³]:	110 (5N)
Ozone resistance:	non resistant
Weather resistance:	non resistant
Oil resistance:	non resistant
Benzine resistance:	non resistant
Acid resistance:	moderately resistant
Strong bases:	resistant
Abrasion resistance:	good suitable

WORKING TEMPERATURE RANGE

Medium	dyn. (stat.)	max.	short-term
Air	-40 (-50) °C	+70 °C	+80 °C

COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	70 °C	25 %

AGEING DIN 53508

Conditions	Hardness	Strength	Elongation
70 h/ 70 °C	+5 Shore A	-10 %	-15 %

ROTA-CURED-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
3665 40206	6.0	1.4	10	S S	0
3665 40208	8.0	1.4	10	S S	0
3665 40210	10.0	1.4	10	S S	0

PRESS-CURED-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
3647 40212	12.0	1.4	5	S S	0
3647 40215	15.0	1.4	5	S S	0
3647 40220	20.0	1.4	5	S S	0
3647 40225	25.0	1.4	5	S S	0
3647 40230	30.0	1.4	5	S S	0
3647 40240	40.0	1.4	5	S S	0
3647 40250	50.0	1.4	5	S S	0

S = smooth

Please Note:

22.8.2003

This catalogue has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this catalogue can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course guarantee the quality of our products according to our general sales conditions, available on request.

Subject to alteration without prior notice – All mentioned properties contained in this catalogue are guiding values representing longterm experience average.

Semperit Technische Produkte Gesellschaft m.b.H. & Co KG
A-2632 Wimpassing, Triester Bundesstraße 26
Telefon +43 2630 310-0*, Telefax +43 2630 310 320
E-Mail: semperflex@semperit.at, Internet: www.semperit.at